


アモルファスシリコン太陽電池 仕様

Model : AM-5909C-T

1. Outside dimensions 外形寸法

Light Receiving Side (受光面)

Overcoat Side (オーハ[®]-コート面)

(dimension : mm)

Note

Glass Substrate Thickness (ガラス基板厚) : 1.6mm ± 0.2

Module Thickness (モジュール厚) : 2.0mm MAX

Accepts normal soldering for bending

(一般の半田を使用してリード[®]線付けが可能です。)

2. Rated Specifications (at 25℃)

Item	Specifications (Initial)
2.1 Open circuit voltage : Voc 開放電圧	Typical 7.7V at 50kLx SS
2.2 Short circuit Current : Isc 短絡電流	Typical 10.9mA at 50kLx SS
2.3 Operating Voltage & Operating Current : Vope - Iope 動作特性	Minimum 4.5V - 7.8mA at 50kLx SS
	Typical 5.0V - 10.1mA at 50kLx SS
	Typical 5.0V - 22.2mA at AM-1.5 100mW/cm ²
2.4 Maximum output : Pmax & optimum operating Volt : Vop optimum operating Current : Iop 最大出力	(reference) 55mW Vop=5.9V Iop=9.3mA at 50kLx SS
	(reference) 116mW Vop=5.9V Iop=19.6mA at AM-1.5 100mW/cm ²
2.5 Working temperature range : Topr 動作温度範囲	-10 to 60℃
2.6 Storage temperature range : Tstg 保存温度範囲	-20 to 70℃

SS: Solar Simulator


アモルファスシリコン太陽電池 仕様

Model : AM-5909CAR-T

1. Outside dimensions 外形寸法

Light Receiving Side (受光面)

Overcoat Side (オーハ[®]-コート面)



(dimension : mm)

Lead Wires : AWG28	
a : 70	b : 70

Note

Glass Substrate Thickness (ガラス基板厚) : 1.6mm ± 0.2

Module Thickness (モジュール厚) : 2.0mm MAX

Wire-Overcoat Thickness : 3.1mm MAX (including Module)
(リード線補正コート厚)

2. Rated Specifications (at 25°C)

Item	Specifications (Initial)
2.1 Open circuit voltage : Voc 開放電圧	Typical 7.7V at 50kLx SS
2.2 Short circuit Current : Isc 短絡電流	Typical 10.9mA at 50kLx SS
2.3 Operating Voltage & Operating Current : Vope-Iope 動作特性	Minimum 4.5V - 7.8mA at 50kLx SS
	Typical 5.0V - 10.1mA at 50kLx SS
	Typical 5.0V - 22.2mA at AM-1.5 100mW/cm ²
2.4 Maximum output : Pmax & optimum operating Volt : Vop optimum operating Current : Iop 最大出力	(reference) 55mW Vop=5.9V Iop=9.3mA at 50kLx SS
	(reference) 116mW Vop=5.9V Iop=19.6mA at AM-1.5 100mW/cm ²
2.5 Working temperature range : Topr 動作温度範囲	-10 to 60°C
2.6 Storage temperature range : Tstg 保存温度範囲	-20 to 70°C


I - V Characteristics

REFERENCE

1.Model : AM-5909

2.Outside Dimension : 60.1mm × 41.3mm

SS:Solar Simulator



*このデータは標準的な出力特性を示すものであり、特性を保証するものではありません。

*The data are meant to show standard electric characteristics only , not intended to guarantee the characteristics.

Panasonic Solar Amorton Co.,Ltd.

2019/7/2



出力の照度依存特性

REFERENCE

Dependence of Output on Illumination

1.Model : AM-5909

2.Outside Dimension : 60.1mm × 41.3mm



*このデータは標準的な出力特性を示すものであり、特性を保証するものではありません。

*The data are meant to show standard electric characteristics only , not intended to guarantee the characteristics.

出力の温度依存特性



REFERENCE

Dependence of Output on Temperature

1.Model : AM-5909

2.Outside Dimension : 60.1mm × 41.3mm

AM-1.5 100mW/cm²



*このデータは標準的な出力特性を示すものであり、特性を保証するものではありません。

*The data are meant to show standard electric characteristics only , not intended to guarantee the characteristics.